



### 600mm Glass Protection Film

#### Description

Ockwells 600mm Glass Protection Film is a 35 micron polythene surface protection film coated with a low tack solvent acrylic adhesive system. Good resistance to moisture, sunlight and variable climatic conditions. This Glass Film is UV stable for up to 6 months. Product Code = 10621992.

#### Applications

Ockwells glass protection film should only be used on plain float glass.

#### Specifications

| No. | Measured Aspect        | Unit   | Specification Requirement  |
|-----|------------------------|--------|--|
| 1   | Backing Film           |        | PE Film  |
| 2   | Adhesive               |        | Acrylic  |
| 3   | Colour                 |        | Transparent Clear  |
| 5   | Thickness              | mm     | 0.035 ± 0.005  |
| 6   | Width                  | mm     | 600 ± 1  |
| 7   | Internal Diameter      | mm     | 76 ± 0.5   |
| 8   | Adhesive Strength      | g/50mm | 380 ± 10%  |
| 10  | Elongation at Break    | %      | ≥ 300  |
| 11  | Temperature Resistance |        | 60°C, 160 hours - no residue glue remains on the glass surface after removal |
| 12  | Length                 | m      | 100 ± 1  |

Ockwells 600mm Glass Protection Film is a 35 micron film that can be left on glass externally for up to 3 months and internally for up to 6 months and should then be replaced.

The company reserves the right to improve products, and any change in specification will result in a re-issue of the information sheet. Please check that you have the latest issue of the information sheet.

#### NEWBURY

Unit 6, Transigo,  
Gables Way, Thatcham,  
Berkshire RG19 4ZA

**T: 01635 876336**

**sales@ockwells.com**

#### WARRINGTON

Unit 29, Melford Court,  
Woolston, Warrington,  
Cheshire WA1 4RZ

**T: 01925 820003**

**sales.warrington@ockwells.com**

#### GLASGOW

Unit 2, 45 Maclellan Street  
Kinning Parkway Estate,  
Glasgow G41 1RR

**T: 0141 427 3366**

**sales.glasgow@ockwells.com**

#### EAST LONDON

Unit E1, Thames View  
Business Centre, Fairview Ind  
Park, Rainham RM13 8BT

**T: 020 7473 8770**

**sales.rainham@ockwells.com**

These properties are the Manufacturer's typical values based on the average of several tests. As the installation and handling of this product is beyond our control, the user must ensure that the product is suitable for the application. Ockwells cannot accept responsibility for any loss or damage that may occur either directly or indirectly by the use of this product. Ockwells also holds the right to change specification data without prior notice.