



HD Glass Protection Film

Description

Ockwells HD Glass Protection Film is a 80 micron polythene surface protection film coated with a low tack solvent acrylic adhesive system. Good resistance to moisture sunlight and variable climatic conditions. This Glass Film is UV stable for up to 12 months. Product Code = 10551498.

Applications

Ockwells glass protection film should only be used on plain float glass.

Specifications

No.	Measured Aspect	Unit	Specification Requirement
1	Backing Film		PE Film
2	Adhesive		Acrylic
3	Colour		Transparent Clear
5	Thickness	mm	0.08 ± 0.005
6	Width	mm	500 ± 1
7	Internal Diameter	mm	76 ± 0.5
8	Adhesive Strength	g/50mm	380 ± 10%
10	Elongation at Break	%	≥ 300
11	Temperature Resistance		60°C, 160 hours - no residue glue remains on the glass surface after removal
12	Length	m	100 ± 1

Ockwells Glass Protection Film is a 80 micron film that can be left on glass externally for up to 6 months and internally for up to 12 months and should then be replaced.

Ockwells HD Glass Protection Film can be applied over most smooth aluminium window frames. The Film may not adhere fully to some textured or matte aluminium window frames and we recommend using our ProtectorGlaze product for such an application.

The company reserves the right to improve products, and any change in specification will result in a re-issue of the information sheet. Please check that you have the latest issue of the information sheet.

Issue 2

NEWBURY

Unit 6, Transigo,
Gables Way, Thatcham,
Berkshire RG19 4ZA
T: 01635 876336
sales@ockwells.com

WARRINGTON

Unit 29, Melford Court,
Woolston, Warrington,
Cheshire WA1 4RZ
T: 01925 820003
sales.warrington@ockwells.com

GLASGOW

Unit 2, 45 Maclellan Street
Kinning Parkway Estate,
Glasgow G41 1RR
T: 0141 427 3366
sales.glasgow@ockwells.com

EAST LONDON

Unit E1, Thames View
Business Centre, Fairview Ind
Park, Rainham RM13 8BT
T: 020 7473 8770
sales.rainham@ockwells.com

These properties are the Manufacturer's typical values based on the average of several tests. As the installation and handling of this product is beyond our control, the user must ensure that the product is suitable for the application. Ockwells cannot accept responsibility for any loss or damage that may occur either directly or indirectly by the use of this product. Ockwells also holds the right to change specification data without prior notice.